

## Solvent Base Opaque Topcoats

Rudd Prod. #	Product	% Solids by Weight	Viscosity Zahn #2 - Secs.	Sag Resistance - Mils	Catalyst Amount Oz/Gal	Pot Life - Hours	Dry to Sand - Minutes	Block Free - Hours	VOC grams/liter	Lbs. HAPs/Lbs. Solids	Shelf Life - Months	Non-Yellowing
<b>Opaque Conversion Varnishes</b>												
310601	MiraVar™ 275 Opaque CV - White	48.7 - 52.1%	16-20	4	6	8	40	24	274*	0.022	12	Yes
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent water and chemical resistance. Exceptional abrasion resistance. Excellent flow out and leveling. Super-Low HAP.										
310745	MiraVar™ Plus 550 Opaque CV - White	58.2 - 60.9%	28-34	5	4	24	40	24	<485*	0.0095	12	Yes
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent water and chemical resistance. Exceptional abrasion resistance. Excellent flow, leveling and sandability. Outstanding hide. Ultra-Low HAP.										
310669	Scion™ 680 Opaque Formaldehyde Free CV - White	44.7 - 46.5%	26	4	4	24	20	24	578	0.019	12	No
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Zero formaldehyde resin technology. Excellent water and chemical resistance. Excellent flow, leveling and sandability. Low odor. Color stable. Super-Low HAP.										
<b>Opaque Pre-Catalyzed Lacquers</b>												
652055	ChromaCat™ 275 Opaque PreCat Lacquer - White	39.6 - 40.5%	19-25	5	n/a	n/a	30	24	273	0.018	6	Yes
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Tough, flexible finish. Excellent moisture resistance. Superior flow, leveling and sandability. Exceptional hide. Super-Low HAP.										
651955	ChromaCat™ 680 Opaque PreCat Lacquer - White	33.7 - 35%	44-50	6	n/a	n/a	25	24	650	0.014	6	Yes
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent water and chemical resistance. Exceptional abrasion resistance. Superior flow, leveling and sandability. Excellent hide. User friendly. Super-Low HAP.										
* Catalyzed VOC content												