

Rudd Prod. #	Product	% Solids by Weight	Viscosity Zahn #2 - Secs.	Sag Resistance - Mills	Dry to Sand - Minutes	Block Free - Hours	VOC grams/liter	Lbs. HAPs/Lbs. Solids	Shelf Life - Months	Non-Yellowing
<b>Clear Conversion Varnish</b>										
310610	CrystalVar™ 275 Water-Clear CV	41.4-44.5%	17-21	4	40	24	237*	0.029	12	Yes
		Excellent water and chemical resistance. Excellent flow and leveling. Exceptional abrasion resistance. Super-Low HAP.								
310599	CrystalVar™ 550 Water-Clear CV	34.7-37.4%	20-25	5	40	24	549*	0.014	12	Yes
		Exceptional abrasion resistance. Excellent water and chemical resistance. Excellent flow, leveling, and sanding. Super-Low HAP.								
310661	CrystalVar™ 680 Water-Clear CV	30.8%	22-28	4	25	24	618*	0.027	12	Yes
		Exceptional abrasion resistance. Excellent water and chemical resistance. Excellent flow, leveling, and sanding. Super-Low HAP.								
310630	Scion™ ZF 680 Clear Formaldehyde Free CV	32.4-34.1	22	4	20	24	632*	0.014	12	No
		Zero Formaldehyde resin technology. Low odor. Color stable. Excellent water and chemical resistance. Excellent sanding properties. Super-Low HAP.								
<b>Clear Pre-Catalyzed Lacquers</b>										
651885	DuraCat™ 275 Water-Clear Pre-catalyzed Lacquer	23.7-25.0%	17-19	5	20	16	274	0.038	6	Yes
		Water-clear, non-yellowing. Excellent abrasion and water resistance. Ultra-Low HAP.								
651810	DuraCat™ 550 Water-Clear Pre-catalyzed Lacquer	26.2-27.7%	17-19	5	20	6	547	0.017	12	Yes
		Water-clear, non-yellowing. Exceptional abrasion and mar resistance. Excellent water and chemical resistance. Ultra-Low HAP.								
651881	CataLuxe™ 680 Clear Pre-catalyzed Lacquer	27.3-28.9%	32-38	5	20	8	671	0.663	12	No
		Slight amber tone. Resistant to yellowing. Exceptional abrasion and mar resistance. Excellent water and chemical resistance. High build. Low HAP.								
651820	ClearBuild™ 680 Water-Clear Pre-catalyzed Lacquer	29.8-31.5%	27-30	4	30	8	653	0.0003	12	Yes
		Water-clear, non-yellowing. Exceptional abrasion and mar resistance. Excellent water and chemical resistance. No HAP.								
653042	UltraClassic™ 680 Water-Clear Pre-catalyzed Lacquer	26.5-27.6%	28-32	5	25	8	667	0.028	12	No
		Water-clear. Resistant to yellowing. Super-Low HAP.								