

Solvent Base Opaque Conversion Varnish

Rudd Prod. #	Product	% Solids by Weight	Viscosity Zahn #2 - Secs.	Sag Resistance - Mills	Catalyst Amount Oz/Gal	Pot Life - Hours	Dry to Sand - Minutes	Block Free - Hours	VOC grams/liter	Lbs. HAPs/Lbs. Solids	Shelf Life - Months	Non-Yellowing
Opaque Conversion Varnish Sanding Sealers (Primers)												
310668	MiraVar™ 275 Opaque CV Sanding Sealer-White	55.7%	30-36	5	4	8	45	n/a	223*	0.015	12	
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Fills edges on MDF. Fast, easy sanding. Super-Low HAP.										
310704	MiraVar™ 550 Opaque CV Sanding Sealer - White	65.5%	70-80 KU	9	4	24	30	n/a	442*	0.247	12	
		Max Tint: 4 fl. oz. of colorant per gallon of coating. Fast, easy sanding. Excellent build. Fills edges on MDF. Ultra-Low HAP.										
310670	Scion™ ZF 550 Opaque Formaldehyde Free CV Sealer - White	52.3%	70 KU	7	4	24	25	n/a	526*	0.016	12	
		Zero Formaldehyde resin technology. Low odor. Color stable. Excellent water and chemical resistance. High build. Super-Low HAP.										
Opaque Conversion Varnish Finish												
310601	MiraVar™ 275 Opaque CV - White	48.7 - 52.1%	16-20	4	6	8	40	24	274*	0.022	12	Yes
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent water and chemical resistance. Exceptional abrasion resistance. Excellent flow out and leveling. Super-Low HAP.										
310745	MiraVar™ Plus 550 Opaque CV - White	58.2 - 60.9%	28-34	5	4	24	40	24	<485*	0.0095	12	Yes
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Excellent water and chemical resistance. Exceptional abrasion resistance. Excellent flow, leveling and sandability. Outstanding hide. Ultra-Low HAP.										
310669	Scion™ 680 Opaque Formaldehyde Free CV - White	44.7 - 46.5%	26	4	4	24	20	24	578	0.019	12	No
		Max Tint: 8 fl. oz. of colorant per gallon of coating. Zero formaldehyde resin technology. Excellent water and chemical resistance. Excellent flow, leveling and sandability. Low odor. Color stable. Super-Low HAP.										